

Envirawood Chemical & Durabilty Testing

ATTRIBUTE	SPECIFICATIONS	TEST METHOD	RESULT
Coating Adhesion	0% Removed	ASTM D3359-97 5b	Passed
Hardness	H Pencil Hardness	ASTM D3363-00	Passed
Solvent Resistance	MEK 200 Rubs	ASTM D5402-93	No Effect
Specular Gloss	60 Degree Measurement	ASTM D2457	88 Gloss Units
Industrial Chemicals	Methyl Ethyl Ketone	ASTM D1308-87 24 hour	No Effect
	Acetone	“ “ “	“ “
	Xylene	“ “ “	“ “
	Concentrated HCL Acid	“ “ “	“ “
	70% Isopropyl Alcohol	“ “ “	“ “
	Turpentine	“ “ “	“ “
	Mineral Spirits	“ “ “	“ “
	Unleaded Gasoline	“ “ “	“ “
	Diesel Fuel	“ “ “	“ “
	Motor Oil	“ “ “	“ “
	Auto Transmission Fluid	“ “ “	“ “
	Anti-Freeze	“ “ “	“ “
	Brake Fluid	“ “ “	“ “
	Armor All	“ “ “	“ “
Domestic Chemicals	H2O/Chlorine Bleach	“ “ “	“ “
	Windex with Ammonia D	“ “ “	“ “
	Pine Sol	“ “ “	“ “
	Tide Liquid Detergent	“ “ “	“ “
	Formula 409	“ “ “	“ “
	Mr. Clean	“ “ “	“ “
	Vinegar	“ “ “	“ “
	Vegetable Oil	“ “ “	“ “
	Crisco	“ “ “	“ “
	Tomato Juice	“ “ “	“ “
	Lemon Juice	“ “ “	“ “
	Grape Juice	“ “ “	“ “
	Milk	“ “ “	“ “
	Red Wine	“ “ “	“ “
	Catsup	“ “ “	“ “
	Coffee	“ “ “	“ “
	Tea	“ “ “	“ “
	Coca Cola	“ “ “	“ “
	Ink	“ “ “	“ “
	Sun Screen	“ “ “	“ “